

July

717.02.2 Bridge Deck Crack Sealant

C. Deck Sealant Sand. Furnish sand for bridge deck crack sealing operations in accordance with manufacturer's recommendations.

Deleted: Furnish silica or garnet sand containing less than 0.5% moisture and in accordance with Table 717-2.¶
TABLE 717-2¶
DECK SEALANT SAND GRADATIONS¶
Percentage By Weight Passing Square Mesh Sieves

Furnish silica or garnet sand containing less than 0.5% moisture and in accordance with Table 717-2.

**TABLE 717-2
DECK SEALANT SAND GRADATIONS**

Percentage By Weight Passing Square Mesh Sieves	
Sieve Size	Percent Passing
No. 8 (2.36 mm)	100
No. 16 (1.18 mm)	80-100
No. 50 (0.30 mm)	0-7